



<b>Date:</b> 02/10/17 <b>Rev.:</b> 00		<b>Material Specification for</b> <b>Ladle Side Wall Brick MK7/30</b>		 IRAN ALLOY STEEL CO.																									
<b>ID code:</b> 7002090039		<b>Area:</b> Ladle		<b>Storage site:</b> 46																									
<b>General properties</b>																													
<b>Basic Components:</b> Magnesita-Carbon			<b>Bonding System:</b> Resin Bonded																										
<b>Classification:</b> Fused Magnesita																													
<b>Chemical composition (wt. %) :</b> <table border="0"> <tr><td>MgO</td><td>Min 96.0</td></tr> <tr><td>CaO</td><td>Max 2.0</td></tr> <tr><td>SiO<sub>2</sub></td><td>Max 0.8</td></tr> <tr><td>Al<sub>2</sub>O<sub>3</sub></td><td>Max 1.5</td></tr> <tr><td>Fe<sub>2</sub>O<sub>3</sub></td><td>Min 1.0</td></tr> <tr><td>C</td><td>7-10</td></tr> </table>			MgO	Min 96.0	CaO	Max 2.0	SiO <sub>2</sub>	Max 0.8	Al <sub>2</sub> O <sub>3</sub>	Max 1.5	Fe <sub>2</sub> O <sub>3</sub>	Min 1.0	C	7-10	<b>Fig.</b>  <b>a=165      b=135      h=177.8      l=100</b>														
MgO	Min 96.0																												
CaO	Max 2.0																												
SiO <sub>2</sub>	Max 0.8																												
Al <sub>2</sub> O <sub>3</sub>	Max 1.5																												
Fe <sub>2</sub> O <sub>3</sub>	Min 1.0																												
C	7-10																												
<b>Sieve analysis /Dimension: -</b>																													
<b>Physical properties :</b> <table border="0"> <tr> <td>Bulk Density</td> <td>2.9-3.1</td> <td>g/cm<sup>3</sup></td> </tr> <tr> <td>Appearance Porosity</td> <td>4-6</td> <td>%</td> </tr> </table>						Bulk Density	2.9-3.1	g/cm <sup>3</sup>	Appearance Porosity	4-6	%																		
Bulk Density	2.9-3.1	g/cm <sup>3</sup>																											
Appearance Porosity	4-6	%																											
<b>Mechanical/Thermal properties:</b> <table border="0"> <tr> <td>Permanent Linear Change</td> <td>-</td> <td>%</td> </tr> <tr> <td>Cold Crushing Strength</td> <td>Min 300</td> <td>kg/cm<sup>2</sup></td> </tr> <tr> <td>Refractoriness Under Load</td> <td>-</td> <td>T<sub>2</sub> , °C</td> </tr> <tr> <td>Hot Modulus of Rupture</td> <td>-</td> <td>kg/cm<sup>2</sup> at 1000 °C</td> </tr> <tr> <td>Thermal Conductivity</td> <td>Max 11.0</td> <td>W/m. k at 1000 °C</td> </tr> <tr> <td>Thermal Expansion</td> <td>-</td> <td>%</td> </tr> <tr> <td>Thermal Shock Resistance</td> <td>-</td> <td>cycle</td> </tr> <tr> <td>Max Service Point</td> <td>1750</td> <td>° C</td> </tr> </table>						Permanent Linear Change	-	%	Cold Crushing Strength	Min 300	kg/cm <sup>2</sup>	Refractoriness Under Load	-	T <sub>2</sub> , °C	Hot Modulus of Rupture	-	kg/cm <sup>2</sup> at 1000 °C	Thermal Conductivity	Max 11.0	W/m. k at 1000 °C	Thermal Expansion	-	%	Thermal Shock Resistance	-	cycle	Max Service Point	1750	° C
Permanent Linear Change	-	%																											
Cold Crushing Strength	Min 300	kg/cm <sup>2</sup>																											
Refractoriness Under Load	-	T <sub>2</sub> , °C																											
Hot Modulus of Rupture	-	kg/cm <sup>2</sup> at 1000 °C																											
Thermal Conductivity	Max 11.0	W/m. k at 1000 °C																											
Thermal Expansion	-	%																											
Thermal Shock Resistance	-	cycle																											
Max Service Point	1750	° C																											
<b>Remark:</b> It is necessary to send the product certification including the chemical analysis , mechanical and physical properties of brick along with each shipment <b>Packing:</b> Pallet <b>Shelf life:</b> <input checked="" type="checkbox"/> 2 Year      NA <input type="checkbox"/> <b>Quality Check:</b> Certificate from supplier and laboratory test																													
<b>Edited:</b> Ehsan Zarezadeh		<b>Checked:</b> Mehdi Eslampour		<b>Approved:</b> Vahid Saffarzadeh																									